



N-Type

Bifacial Module with Double Glass

Type: DMXXXM10RT-B54HBB-L

Power Range: 435 - 450 W Max. Efficiency: 22.52 %





Bifacial Module Application

Up to 25 % higher electricity yields due to active cell technology in bifacial glass/glass modules on both sides.



Better Performance

Our modules perform better on sunny and hot days thanks to its optimized temperature coefficient.



Excellent Low Light Performance

Our modules can also provide higher power output under low light conditions, such as sunset, cloudy, or dawn.



Excellent Quality

More than 40 years' experience of manufacturing and intensive quality tests above the IEC standard ensures reliable modules and a secured investment.



Assumption of Environmental, Social and Governance Responsibility (ESG)

DMEGC stands for his responsibility. Production is certified according to SA 8000 (ILO standards).



Certifications


SA 8000 ILO Standards. Social responsibility standards

ISO 9001 Quality management system

ISO 14001 Environmental management system

ISO 45001 Occupational health and safety management system

ISO 50001 Energy management system

























DMXXXM10RT-B54HBB-L



Module Specification

Cell Type	N -type Mono-crystalline , 108 (6x18)	
Dimensions (mm)	1762 x 1134 x 30	
Weight (kg)	20.4	
Front Cover	1.6 mm heat strengthened glass with anti -reflective coating	
Rear Cover	1.6 mm heat strengthened glass	
Junction Box	3 Diodes, IP68 according to IEC 62790	
Cables	4 mm² solar cable, 1.1 m or Customized Length	
Connector Type PV-ZH202B or MC4-EVO 2A (1500V)		



Electrical Specifications¹

Module Type	DM435M10R	T-B54HBB-L	DM440M10RT-B54HBB-L		DM445M10RT-B54HSBB-L		DM450M10RT-B54HBB-L	
Testing Condition	STC ²	NMOT ³	STC	NMOT	STC	NMOT	STC	NMOT
Maximum Power (Pmax/W)	435	327	440	331	445	335	450	339
Maximum Power Current (Imp/A)	13.33	10.78	13.40	10.83	13.47	10.89	13.54	10.95
Maximum Power Voltage (Vmp/V)	32.64	30.49	32.84	30.67	33.04	30.86	33.24	31.05
Short-circuit Current (Isc/A)	13.83	11.14	13.90	11.19	13.97	11.25	14.04	11.31
Open-circuit Voltage (Voc/V)	39.20	37.13	39.40	37.32	39.60	37.51	39.80	37.70
Module Efficiency STC (%)	21.8		22.0		22.3		22.5	

¹ Measurements according to IEC 60904-3, Measurement tolerance: ISC: ±4%,VOC: ± 3%, Bifaciality: 80% ± 10%

BIFACIAL OUTPUT - REARSIDE POWER GAIN

 10 %	Pmax (STC)	479	484	490	495
20 %	Pmax (STC)	522	528	534	540
30 %	Pmax (STC)	566	572	579	585

Certifications and Warranty

	IEC 61215, IEC 61730
	Ammonia Corrosion Test: IEC 62716
Certifications	Salt Mist Corrosion Test: IEC 61701
	PID (IEC TS 62804); LeTID (IEC TS 63342)
	Dust & Sand (IEC 60068)
WEEE Registration No.	DE 50188598
Product Warranty	25 years
Peak Power Warranty	30 years linear warranty

^{1.)} First year: min. 99 %. 2.) From the 2nd year: Max. 0.4 % degradation annually. 3.) Min. 87.4 % in the 30th year.

Operating conditions


Operating Temperature (°C)	-40 to +85		
Maximum System Voltage(V)	1500 DC (IEC)		
Overcurrent protection rating (A)	30		
Power Performance Tolerance (%)	0 / +3		
Protection class	II		
Max. Test Load, Push/Pull (Pa)	Snow 5400 / Wind 2400		
Max. Design Load, Push/Pull (Pa)	3600 / 1600		
	·		

Temperature Characteristics

Nominal Module Operating Temperature (NMOT)	45 ± 2°C
Temperature Coefficient of Pmax (%/ $^{\circ}$ C)	-0.29
Temperature Coefficient of Voc (%/ °C)	-0.25
Temperature Coefficient of Isc (%/ °C)	+0.048

Packaging

Container	40' HQ
Pallet Dimensions(mm)	1800 × 1140 × 1250
Pieces per Pallet	36
Pieces per Container	936



Statement: The installation instructions and the warranty conditions must be followed. Due to technological progress, product parameters will be adjusted accordingly. When signing the contract, the latest data of the company shall



errors excepted. Status: 10/2023, Document: EN_DS-M10RT-B54HBB-L-202310_3

All information in this data sheet corresponds to EN 50380. Changes and

² STC (Standard Test Condition): Radiation 1000 W/m², Module temperature 25 °C, AM = 1.5 ³ NMOT: Radiation 800 W/m², Ambient temperature 20 °C, AM = 1.5, Wind Speed 1 m/s